

Technical Data Sheet

EverTherm SC Series is a thermally conductive silicone tape offering high temperature capability and conformability. Fiberglass fabric supports the thermally conductive silicone rubber impregnation and adds dimensional stability and resistance. This puncture thin material keeps thermal resistance low and save space while providing electrical isolation.



Material Properties

- Assembly time reduced by 70% over grease & mica systems
- Puncture resistance; high thermal conductivity
- Electrically isolates power sources from heat sink devices
- Resists high pressure and deterioration
- Optional Adhesive available for ease of install
- UL94V-0 flammability rating, ROHS, halogen free
- Easy to assemble

Applications

- ✓ Automotive electronics
- ✓ Adapter
- ✓ Communication equipment
- ✓ Motor Controller
- ✓ High pressure interface
- Semiconductor Optoelectronic Products



	00			
V/SI	C9	(0)	(0)	G

Color	Brick Red	Visual				
Base	Fiberglass	* * *				
Thickness (mm)	0.2~0.5mm	ASTM D751				
Density (g/cm³)	2.2	ASTM D297				
Hardness (Shore A)	45	ASTM D2240				
Tensile Strength (psi)	450	ASTM D412				
Applicable tempure/ °C	-50 to 200୧	* * *				
Electrical						
Dielectric Breakdown Voltage@AC	>4000V	ASTM D149				
Dielectric constant (1MHz)	5.5	ASTM D150				
Volume resistivity (Ω.cm)	5.0 X 10 ¹³	ASTM D257				
Fire rating	V-0	UL 94				
Thermal conductive						
Thermal conductivity(W/m.k)	2.0	ASTM D5470				
RoHS	PASS	IEC 62321				
Halogen	PASS	EN14582				
REACH	PASS EN14372					

Test fixtures using ASTM D5470. Recorded values include interface thermal resistance. These values are for reference only. The actual application performance is directly related to the applied surface roughness, flatness and pressure.

CR Technology, Inc

💿 55 Chase St. Methuen,

Massachusetts 01844

- sales@crtechinc.com
- 978.681.5300

Note: The information provided herein is accurate at time of publication. It is the responsibility of the end-user to confirm compliance to their application. All test data is typical. Therefore, these recommendations and data are for reference only and not as a product warranty.