## Nylon Fasteners

## Machine Screws



		N	ION PAN	HEAD MAC	HINE SCRE	NS			
Nominal Size	A		Н		J		т		
	Head Diameter		Height of Head		Width of Slot		Depth of Slot		
	Мах	Min	Мах	Min	Max	Min	Max	Min	
1	.142	.130	.046	.038	.026	.019	.027	.018	
2	.167	.155	.053	.045	.031	.023	.031	.022	
4	.219	.205	.068	.058	.039	.031	.040	.030	
6	.270	.256	.082	.072	.048	.039	.050	.037	
8	.322	.306	.096	.085	.054	.045	.058	.045	
10	.373	,357	.110	.099	.060	.050	.068	.053	
1/4	.492	.473	.144	.130	.075	.064	.087	.070	
Tolerance on Length	Nominal Screw Size	Nominal Screw Length							
		Up to 1/2 in., incl.		Over 1/2 to 1 in., incl.		Over 1 to 2 in., incl.		Over 2 in.	
	1 thru 10	-0.02		-0.03		-0.06		-0.09	
	1/4	-0.03		-0.03		-0.06		-0.09	
								•	
Description		An externally threaded fastener with a head that has slightly rounded sides, a flat top and a flat underside.							
Applications/ Advantages		To be used with internally threaded nylon fasteners in applications that require corrosion resistance or electrical insulation. Nylon's other advantages include: resistance to greases and oils; a low coefficient of friction; ability to maintain its torque strength when exposed to a wide range of temperatures.							
Material		Nylon 6/6							
Hardness		Rockwell M80							
Tensile, shear	and torque data	a is offered for i		rposes only. This parts in the actu	s data should not a	be used to set i	specification im	its. It is always	
Tensile Test (Break Pounds)	)	2-56: 19 lbs.; 4-40: 41 lbs.; 6-32: 69 lbs.; 8-32: 108 lbs.; 10-24: 149 lbs.; 10-32: 165 lbs.; 1/4-20: 312 lbs.							
Double Shear (Break Pounds)	, 2	2-56: (No test); 4-40: 50 lbs.; 6-32: 97 lbs.; 8-32: 164 lbs.; 10-24: 257 lbs.; 10-32: 241 lbs.; 1/4-20: 432 lbs.							
Maximum Torqu (before deformation)		2-56: (No test); 4-40: 12-16 in. oz.; 6-32: 18-20 in. oz.; 8-32: 2-3 in. lbs.; 10-24: 2-4 in. lbs.; 10-32: 3-4 in. lbs.; 1/4-20: 9-10 in. lbs.							
Thermal Properties		Melting Point: 500° F Continuous Use Temperature: 185° F							