


Core **Toroid 13/7.9/6.4**



| Effective parameters | | | |
|----------------------|-----------------------|-------|------------------|
| | Parameter | Value | Unit |
| $\Sigma(I/A)$ | core factor (C_1) | 2.21 | mm^{-1} |
| V_e | effective volume | 442 | mm^3 |
| L_e | effective length | 31.2 | mm |
| A_e | effective area | 14.1 | mm^2 |
| m | mass of core | ≈ 2.2 | g/pcs |

Epoxy coating DC isolation voltage 1500.

Maximum operating temperature of the coating is 200°C.

Dimensions (mm)

| Cores | OD | ID | H | |
|--------------|-----------|----------|-------|--------------|
| TX13/7.9/6.4 | 13.35 max | 7.27 min | 7 max | Epoxy Coated |

Core data

| Cores | Material | AI (nH/turns ²) | AI tolerance | μe |
|--------------|--------------|-----------------------------|--------------|---------------|
| TX13/7.9/6.4 | 3C94 | 1400 | ± 25% | ≈ 2300 |
| TX13/7.9/6.4 | 3E10 | 6100 | ± 20% | ≈ 10000 |
| TX13/7.9/6.4 | 3E12 | 7320 | ± 30% | ≈ 12000 |
| TX13/7.9/6.4 | 3E27 | 3350 | ± 25% | ≈ 5500 |
| TX13/7.9/6.4 | 3E6 (3E10-M) | 6100 | ± 30% | ≈ 10000 |
| TX13/7.9/6.4 | 3E65 | 3170 | ± 25% | ≈ 5200 |