Static Shielding Bag 1300 Series

This transparent metal-in static shielding bag is designed to provide a static safe environment for ESD sensitive electronic devices. A stronger polyester layer helps prevent punctures. Bags are printed with an ESD protective symbol and a lot code for traceability. The bags are heat sealable. ZipTop and other custom features are available.

SCS Static Shielding Bags 1300 are manufactured from a polyester, metal, polyethylene laminate. The polyester dielectric in concert with the metal layer provides shielding of Electrostatic Discharge (ESD) and minimizes the penetration of electrostatic and electric fields.





Meets ANSI/ESD S20.20 Packaging Standard, ANSI/ESD S541, and Static Control Bag ANSI/ESD S11.4 Level 3



Physical	Typical Value	Testing Method
Tensile Strength	8100 PSI, 55 MPa	ASTM D882
Puncture Resistance	22 lbs, 98 N	MIL-STD-3010C Method 2065
Seal Strength	15 lbs, 66 N	ASTM D882
Thickness	3.2 mils, 0.0813 mm +/-10%	MIL-STD-3010C Method 1003
Marking Adhesion	Pass	IPC-TM-650 2.4.1
Transparency	40%	Tobias
Electrical	Typical Value	Testing Method
Discharge Shielding	<20 nJ	ANSI/ESD STM11.31
Surface Resistance - Interior	1 x 10 ⁴ to < 1 x 10 ¹¹ ohms	ANSI/ESD STM11.11
Surface Resistance - Exterior	1 x 10 ⁴ to < 1 x 10 ¹¹ ohms	ANSI/ESD STM11.11
Cleanliness	Typical Value	Testing Method
Silicone	Not Detected	FTIR
Heat Sealing Conditions	Typical Value	
Temperature	375°F, 190°C	
Time	0.5 - 3.5 seconds	
Pressure	30 – 70 PSI, 206 - 482 KPa	

Bag is free of amines, silicones and heavy metals.

This product is intended for commercial use only. This product is not on the Qualified Product Listing under the Defense Standardization Program.

Made in the United States of America with Globally Sourced Materials.

Specifications and procedures subject to change without notice.

1300 SERIES STATIC SHIELDING BAG

926 JR Industrial Drive, Sanford, NC 27332	DRAWING	DATE
WEB SITE: <u>StaticControl.com</u>	NUMBER	July
PHONE (919) 718-0000	1300 Series	2016