# 860



## Silicone Heat Transfer Compound

860 is a thermal paste designed to reduce thermal resistance between irregular metal surfaces. Coupled with reasonable thermal conductivity, it has a soft consistency and a wide operating temperature range, making it an ideal thermal paste for CPU applications.

This silicone-based thermal paste is mostly used to improve heat flow between heat sinks and heatgenerating components, such as CPUs, GPUs, LEDs, motors, and power components.



#### Features & Benefits

- · High dielectric strength
- Excellent corrosion resistance
- Non-bleeding heat transfer paste
- Non-electrically conductive
- Long service life

#### **Available Packaging**

| Cat. No.  | Packaging | Net Vol. | Net Wt. |
|-----------|-----------|----------|---------|
| 860-4G    | Pouch     | 1.7 mL   | 4 g     |
| 860-60G   | Jar       | 25 mL    | 60 g    |
| 860-150G  | Tube      | 62.5 mL  | 150 g   |
| 860-1P    | Jar       | 470 mL   | 1.13 kg |
| 860-3.78L | Pail      | 3.78 L   | 9.07 kg |

#### **Storage and Handling**

Store between 0 and 30 °C in a dry area, away from sunlight (see SDS).

#### **Contact Information**

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772 International: +(1) 905-331-1396 Europe: +(44)1663 362888

### **Properties**

| Color   | White                  |         |
|---|------------------------|---------|
| Filler  | Zinc oxide             |         |
| Base Material                                   | Silicone oil           |         |
| Density   | 2.4                    | g/mL    |
| Viscosity                                       | 490                    | Pa·s    |
| Resistivity                                     | 1.5 x 10 <sup>15</sup> | Ω·cm    |
| Thermal Conductivity @ 25 °C                    | 0.7                    | W/(m·K) |
| Evaporation Loss, 22 h @ 165 °C                 | 0.1                    | %       |
| Oil Separation, 30 h @ 165 °C                   | 0.7                    | %       |
| Worked Penetration, ½ scale                     | 303                    |         |
| Water Washout @ 38 °C,<br>Bearing Dried @ 77 °C | 0.1                    | %       |
| Dielectric Strength                             | 400                    | V/mil   |
| Dielectric Constant @ 1 000 cps                 | 3.8                    |         |
| Dissipation Factor @ 1 000 cps                  | 0.003                  |         |
| Service Temperature Range                       | -40–200                | °C      |

#### **Disclaimer**

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.