Rev: 2021-09-10

GL4500P SeriesESD Inspection Gloves - Palm Coated

ESD inspection gloves are worn when handling ESD susceptible items when cleanliness is a priority.

Transforming Technologies ESD inspection gloves are designed to be worn when handling ESD susceptible items. They are made with a dissipative nylon to reduce charge generation. Polyurethane coated palms allow for excellent grip and increases breathability. A seamless fine gauge knit, a finished rolled cuff and uncoated back are designed for comfort and breathability. Transforming Technologies' ESD inspection gloves may be laundered for repeated use. Sold in packs of 12 pairs.

ESD Properties:

They are made with a dissipative nylon to reduce charge generation. The gloves have a resistance of 10⁶ ~ 10⁸ and ESD properties are not effected by laundering. The gloves meets or exceeds requirements of ANSI/ESD S20.20 and ANSI/ESD S-6.1.

Clean Applications:

-:::--:

Composition:

Carbon 5.1% Polyamide 10 %

Elastic 10.4%

Nylon:74.5%

The GL4500P series are ideal for applications that require clean assembly. They reduce the transfer of fingerprints, oils, and other skin contaminants when handling sensitive items. The gloves are made with a seamless, fine gauge knit nylon which results in a low-linting properties.

Specification Fabric:	IS: Nylon &Con-	Part Numbers:		
	ductive Carbon	Item No.	Size	Length
Grip:	Palm Coated with Polyurethane	GL4501P GL4502P GL4503P	X-Small Small Medium	8" 8" 8"
Cuff:	Finished Rolled Cuff	GL4504P GL4505P GL4506P	Large X-Large 2X-Large	8.5" 8.75" 9"
Resistance:	10^6-10^8 per ANSI/ESD SP15.1		. 0	_



Features

- ESD gloves are to be worn when handling static sensitive items
- Coated Palms for Excellent Grip
- Breathable and Comfortable
- Fine gauge Knit Nylon and Carbon
- Finished Rolled Cuff
- Washable







This document is prepared for our customers as a service, and is to the best of our knowledge true and accurate. However, it is understood and agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.