"PGS" Graphite Sheets

Type: **EYG**

"PGS (Pyrolytic Graphite Sheet)" is a thermal interface material which is very thin, synthetically made, has high thermal conductivity, and is made from a higly oriented graphite polymer film. It is ideal for providing thermal management/heatsinking in limited spaces or to provide supplemental heat-sinking in addition to conventional means. This material is flexible and can be cut into customizable shapes.

"SSM(Semi-Sealing Material)" is the product which is compounding PGS Graphite sheet and High thermal conductive Elastomer resin. It has a function to absorb heat by resin and release the heat by utilizing high thermal conductivity of PGS Graphite sheet. It also enables taking better attachment to the component which has different height on the electronic board, reducing stress to the electronic board.



Features

- Excellent thermal conductivity : 700 to 1950 W/(m·K) (2 to 5 times as high as copper, 3 to 8 time as high as aluminum)
- Lightweight: Specific gravity : 0.85 to 2.13 g/cm³ (1/4 to 1/10 of copper, 1/1.3 to 1/3 of aluminum in density)
- Flexible and easy to be cut or trimmed. (withstands repeated bending)
- Low thermal resistance
- Low heat resistance with flexible Graphite sheet (SSM)
- Low repulsion and easy to keep the product's shape after attaching (SSM)
- Siloxane Free(SSM)
- High dielectric voltage : 17 kVac/mm (SSM)
- RoHS compliant

Recommended applications

- Smart phones, Mobile phones, DSC, DVC, Tablet PCs, PCs and peripherals, LED Devices
- Semiconductor manufacturing equipment (Sputtering, Dry etching, Steppers)
- Optical communications equipment

12

Μ

Explanation of Part Numbers

PGS only (EYGS******)





Thermally conductive elastomer processing (EYGE********)



"PGS" Graphite Sheets

Characteristics of PGS Graphite Sheets							
Thickness		100 µm	70 µm	50 µm	40 µm		
THICKNESS		0.10±0.03 mm	0.07±0.015 mm	0.050±0 .015 mm	0.040±0 .012 mm		
Density		0.85 g/cm ³	1.21 g/cm ³	1.70 g/cm ³	1.80 g/cm ³		
Thermal conductivity	a-b plane	700 W/(m·K)	1000 W/(m·K)	1300 W/(m·K)	1350 W/(m·K)		
Electrical conductivity		10000 S/cm	10000 S/cm	10000 S/cm	10000 S/cm		
Extensional strength	Extensional strength		20.0 MPa	20.0 MPa	25.0 MPa		
	a-b plane	9.3×10 ⁻⁷ 1/K	9.3×10 ⁻⁷ 1/K	9.3×10 ⁻⁷ 1/K	9.3×10 ⁻⁷ 1/K		
Expansion coefficient	c axis	3.2×10⁻⁵ 1/K	3.2×10⁻⁵ 1/K	3.2×10⁻⁵ 1/K	3.2×10⁻⁵ 1/K		
Heat resistance*		400 °C					
Bending(angle 180,R5	5)	10000 cycles					
				1			
Thickness		25 µm	17 µm	10 µm			
THICKIC55		0.025±0 .010 mm	0.017±0 .005 mm	0.010±0 .002 mm			
Density		1.90 g/cm ³	2.10 g/cm ³	2.13 g/cm ³	-		
Thermal conductivity a-b plane		1600 W/(m·K)	1850 W/(m·K)	1950 W/(m·K)	•		
Electrical conductivity		20000 S/cm	20000 S/cm	20000 S/cm	-		
Extensional strength		30.0 MPa	40.0 MPa	40.0 MPa	•		
	a-b plane	9.3×10 ⁻⁷ 1/K	9.3×10 ⁻⁷ 1/K	9.3×10 ⁻⁷ 1/K	-		
Expansion coefficient				1			

3.2×10⁻⁵ 1/K

400 °C 10000 cycles 3.2×10⁻⁵ 1/K

3.2×10⁻⁵ 1/K

	-	 -
Heat resistance*		
Ponding(angle 190 PE)	

Bending(angle 180,R5)

Expansion coefficient

Withstand temperature refers to PGS only. (Lamination material such as PET tape etc. is not included) *

c axis

** Values are for reference, not guaranteed.

		SM (Elastomer)	I.	[
Thick	iness	1 mm	2 mm	3 mm		
Specif	ic heat		1.4 J/(g·C)			
Den	nsity		1.88 g/cm ³			
Thermal co	onductivity		1.6 W/(m·K)**			
	100 kPa	7.53 (C·cm²)/W	14.82 (C·cm ²)/W	19.48 (C·cm ²)/W		
Thermal resistance	200 kPa	6.71 (C·cm²)/W	13.17 (C·cm²)/W	16.01 (C·cm ²)/W		
resistance	300 kPa	5.90 (C·cm²)/W	10.73 (C·cm ²)/W	11.38 (C·cm ²)/W		
	100 kPa	4.93 %	4.05 %	4.43 %		
Compressibility	200 kPa	9.58 %	8.66 %	14.04 %		
	300 kPa	18.41 %	22.13 %	40.49 %		
Resis	stivity		> 10×10 ¹⁴ Ω·cm			
Dielectric	c voltage	> 17 kVac/mm				
Hardness (Type E)		39				
Adhesive force	SUS		39 mN/cm			
	Aluminum		31 mN/cm			
	Glass		38 mN/cm			

* Characteristics refer to Elastomer resin only.

** Typical values, not guaranteed.



Electric field shield performance

Layered structure of PGS





Design and specifications are each subject to change without notice. Ask factory for the current technical specifications before purchase and/or use. Should a safety concern arise regarding this product, please be sure to contact us immediately.

Lamination type/Composition example

• Standard series (PGS 100, 70, 50, 40, 25, 17, 10 μm)

Туре		PGS Only		Adhesive Type	
	туре	S type	A-A type	A -M type	A -F type
Front face –		-	-	-	-
	Rear face –		Insulative adhesion type 30 µm	Insulative thin adhesion type 10 µm	Insulative thin adhesion type 6 µm
	Structure	PGS Graphite sheet	PGS Graphite sheet	PGS Graphite sheet	PGS Graphite sheet
	Features	High Thermal Conductivity High Flexibility Low Thermal Resistance Available up to 400 °C Conductive Material	 With insulation material on one side With strong adhesive tape for putting chassis Withstanding Voltage : 2 kV 	With insulation material on one side Low thermal resistance comparison with A-A type Withstanding Voltage : 1 kV	 With insulation material on one side Low thermal resistance comparison with A-A type
Withstand temperature		400 °C	100 °C	100 °C	100 °C
S	itandard size	115 × 180 mm	90 × 115 mm	90 × 115 mm	90 × 115 mm
Μ	1aximum size	180 × 230 mm (25 µm to)	115 × 180 mm	115 × 180 mm	115 × 180 mm
100	Part No.	EYGS121810	EYGA091210A	EYGA091210M	EYGA091210F
μm	Thickness	100 µm	130 µm	110 µm	106 µm
70	Part No.	EYGS121807	EYGA091207A	EYGA091207M	EYGA091207F
μm	Thickness	70 µm	100 µm	80 µm	76 µm
50	Part No.	EYGS121805	EYGA091205A	EYGA091205M	EYGA091205F
μm	Thickness	50 µm	80 µm	60 µm	56 µm
40	Part No.	EYGS121804	EYGA091204A	EYGA091204M	EYGA091204F
μm	Thickness	40 µm	70 µm	50 µm	46 µm
25	Part No.	EYGS121803	EYGA091203A	EYGA091203M	EYGA091203F
μm	Thickness	25 µm	55 µm	35 µm	31 µm
17	Part No.	_	EYGA091202A	EYGA091202M	EYGA091202F
μm	Thickness	-	47 µm	27 µm	23 µm
10	Part No.	_	EYGA091201A	EYGA091201M	EYGA091201F
μm	Thickness	-	40 µm	20 µm	16 µm

Turno			Laminated type (Ins	sulation & Adhesive)	
	Туре	A-PA type	A-PM type	A-DM type	A-DF type
	Front face	Polyester tape standard type 30 µm	Polyester tape standard type 30 µm	Polyester tape thin type 10 µm	Polyester tape thin type 10 µm
	Rear face	Insulative adhesion type 30 µm	Insulative thin adhesion type 10 μ m	Insulative thin adhesion type 10 µm	Insulative thin adhesion type 6 µm
	Structure		PGS Polyester(PET) Graphite sheet Polyester(PET) tape 30 µm Acrylic Adhesive tape 10 µm Separating paper	PGS Graphite sheet Polyester(PET) tape 10 µm Acrylic Adhesive tape 10 µm Separating paper	PGS Polyester(PET) Graphite sheet Polyester(PET) tape 10 µm Acrylic Adhesive tape 6 µm Separating paper
Features		• With insulation material on both side • Withstanding Voltage PET tape : 4 kV Adhesive Tape : 2 kV	•With insulation material on both side •Withstanding Voltage PET tape : 4 kV Adhesive Tape : 1 kV	· With insulation material on both side · Withstanding Voltage PET tape : 1 kV Adhesive Tape : 1 kV	•With insulation material on both side •Withstanding Voltage PET tape : 1 kV
Withst	Withstand temperature 100		100 °C	100 °C	100 °C
S	tandard size	90 × 115 mm	90 × 115 mm	90 × 115 mm	90 × 115 mm
M	aximum size	115 × 180 mm	115 × 180 mm	115 × 180 mm	115 × 180 mm
100	Part No.	EYGA091210PA	EYGA091210PM	EYGA091210DM	EYGA091210DF
μm	Thickness	160 µm	140 µm	120 µm	116 µm
70	Part No.	EYGA091207PA	EYGA091207PM	EYGA091207DM	EYGA091207DF
μm	Thickness	130 µm	110 µm	90 µm	86 µm
50	Part No.	EYGA091205PA	EYGA091205PM	EYGA091205DM	EYGA091205DF
μm	Thickness	110 µm	90 µm	70 µm	66 µm
40	Part No.	EYGA091204PA	EYGA091204PM	EYGA091204DM	EYGA091204DF
μm	Thickness	100 µm	80 µm	60 µm	56 µm
25	Part No.	EYGA091203PA	EYGA091203PM	EYGA091203DM	EYGA091203DF
μm	Thickness	85 µm	65 µm	45 µm	41 µm
17	Part No.	EYGA091202PA	EYGA091202PM	EYGA091202DM	EYGA091202DF
μm	Thickness	77 µm	57 µm	37 µm	33 µm
10	Part No.	EYGA091201PA	EYGA091201PM	EYGA091201DM	EYGA091201DF
μm	Thickness	70 µm	50 µm	30 µm	26 µm

Please contact us for other lamination type product.
 Withstanding Voltages are for reference, not guaranteed.

Design and specifications are each subject to change without notice. Ask factory for the current technical specifications before purchase and/or use. Should a safety concern arise regarding this product, please be sure to contact us immediately.

Lamination type/Composition example

• High heat resistance series (PGS 100, 70, 50, 40, 25, 17, 10 μm)

	Туре	High heat re	sistance type	
	туре	A-V type	A-RV type	
	Front face	-	High heat resistance and insulation type 13 µm	
	Rear face	High heat resistance and insulation adhesion type 18 µm	High heat resistance and insulation adhesion type 18 µm	
Structure Heat-resistance Acrylic adhesive tape 18 µm Separating paper		Graphite sheet	PGS Heat-resistance Graphite sheet PEEK tape 13 µm Heat-resistance Acrylic adhesive tape 18 µm Separating paper	
	Features tape on one side tape • Withstanding Voltage Adhesive tape • W • 2 kV F		 With high heat resistance and insulation tape on both side Withstanding Voltage PEEK tape : 2 kV Adhesive tape : 2 kV 	
Withst	tand temperature	150 °C	150 °C	
St	tandard Size	90 × 115 mm	90 × 115 mm	
M	laximam size	115 × 180 mm	115 × 180 mm	
100	Part No.	EYGA091210V	EYGA091210RV	
μm	Thickness	118 µm	131 µm	
70	Part No.	EYGA091207V	EYGA091207RV	
μm	Thickness	88 µm	101 µm	
50	Part No.	EYGA091205V	EYGA091205RV	
μm	Thickness	68 µm	81 µm	
40	Part No.	EYGA091204V	EYGA091204RV	
μm	Thickness	58 µm	71 µm	
25	Part No.	EYGA091203V	EYGA091203RV	
μm	Thickness	43 µm	56 µm	
17	Part No.	EYGA091202V	EYGA091202RV	
μm	Thickness	35 µm	48 µm	
10	Part No.	EYGA091201V	EYGA091201RV	
μm	Thickness	28 µm	41 µm	

* Please contact us for other lamination type product.

** Withstanding Voltages are for reference, not guaranteed.

• Standard series (SSM)

	Туре	E-6 type	E-8 type	E-9 type
Elast	tomer thickness	1.0 mm	2.0 mm	3.0 mm
	Structure	Acrylic Adhesive Lape 1.0 mm	PGS PET tape Graphite Sheet 10 µm Acrylic Adhesive tape Elastomer 2.0 mm	PGS PET tape Graphite Sheet 10 µm Acrylic Adhesive tape Elastomer 3.0 mm
	Features	 Soft and low thermal resistance (Elastomer) Low repulsion Withstanding Voltage : 1.7 kV 	 Soft and low thermal resistance (Elastomer) Low repulsion Withstanding Voltage : 1.7 kV 	 Soft and low thermal resistance (Elastomer) Low repulsion Withstanding Voltage : 1.7 kV
Withst	tand temperature	100 °C	100 °C	100 °C
St	tandard Size	90 × 115 mm	90 × 115 mm	90 × 115 mm
70	Part No.	EYGE0912XB6D	EYGE0912XB8D	EYGE0912XB9D
μm	Thickness	1.09 mm	2.09 mm	3.09 mm
25	Part No.	EYGE0912XD6D	EYGE0912XD8D	EYGE0912XD9D
μm	Thickness	1.05 mm	2.05 mm	3.05 mm

Design and specifications are each subject to change without notice. Ask factory for the current technical specifications before purchase and/or use. Should a safety concern arise regarding this product, please be sure to contact us immediately.

"PGS" Graphite Sheets

Panasonic

	N	linimum order		
Item	Туре	Part No.	Size	Minimum order
		EYGS091210	90×115 mm	20
	S type 100 µm		10	
	roo pini	EYGS182310	180×230 mm	10
	S type	EYGS091207	90×115 mm	20
	5 type 70 μm	EYGS121807	115×180 mm	10
	roμm	EYGS182307	180×230 mm	10
DOC Orachita Chast	Cture	EYGS091205	90×115 mm	20
PGS Graphite Sheet Only	S type 50 µm	EYGS121805	115×180 mm	10
Chiy	ου μπ	EYGS182305	180×230 mm	10
	Citure	EYGS091204	90×115 mm	20
	S type 40 µm	EYGS121804	115×180 mm	10
	40 μΠ	EYGS182304	180×230 mm	10
	0 to 20	EYGS091203	90×115 mm	20
	S type 25 µm	EYGS121803	115×180 mm	10
	20 µm	EYGS182303	180×230 mm	10
	A-A type	EYGA091207A	90×115 mm	20
	70 µm	EYGA121807A	115×180 mm	10
	A-A type 25 μm	EYGA091203A	90×115 mm	20
		EYGA121803A	115×180 mm	10
	A-A type 17 µm	EYGA091202A	90×115 mm	20
PGS 70, 25, 17 µm		EYGA121802A	115×180 mm	10
Adhesive Type [Standard series]	A-M type 70 µm	EYGA091207M	90×115 mm	20
		EYGA121807M	115×180 mm	10
	A-M type	EYGA091203M	90×115 mm	20
	25 µm	EYGA121803M	115×180 mm	10
	A-M type	EYGA091202M	90×115 mm	20
	17 µm	EYGA121802M	115×180 mm	10
	A-PA type	EYGA091207PA	90×115 mm	20
	70 µm	EYGA121807PA	115×180 mm	10
	A-PA type	EYGA091203PA	90×115 mm	20
	25 µm	EYGA121803PA	115×180 mm	10
	A-PA type	EYGA091202PA	90×115 mm	20
	17 µm	EYGA121802PA	115×180 mm	10
	A-PM type	EYGA091207PM	90×115 mm	20
PGS 70, 25, 17 µm	70 µm	EYGA121807PM	115×180 mm	10
Laminated Type	A-PM type	EYGA091203PM	90×115 mm	20
(Insulation & Adhesive)	25 µm	EYGA121803PM	115×180 mm	10
[Standard series]	A-PM type	EYGA091202PM	90×115 mm	20
	17 µm	EYGA121802PM	115×180 mm	10
	A-DM type	EYGA091207DM	90×115 mm	20
	70 µm	EYGA121807DM	115×180 mm	10
	A-DM type	EYGA091203DM	90×115 mm	20
	25 µm	EYGA121803DM	115×180 mm	10
	A-DM type	EYGA091202DM	90×115 mm	20
	17 µm	EYGA121802DM	115×180 mm	10

Only S type supports 180×230 mm size. (PGS thickness of 17 µm, 10µm does not support as single item)
** PGS of 10 µm, 40 µm, 50 µm type is also possible to be made as lamination type.
*** The above-listed part number is sample part number for testing.
**** Please contact us about your request of custom part number which will be arranged separately.
***** Please contact us if quantity is below Minimum Order Quantity.

Minimum order					
Item	Туре	Part No.	Size	Minimum order	
	A-V type	EYGA091207V	90×115 mm	20	
	70 µm	EYGA121807V	115×180 mm	10	
	A-V type	EYGA091203V	90×115 mm	20	
	25 µm	EYGA121803V	115×180 mm	10	
	A-V type	EYGA091202V	90×115 mm	20	
PGS 70, 25, 17 µm	17 µm	EYGA121802V	115×180 mm	10	
[High heat resistance type]	A-RV type	EYGA091207RV	90×115 mm	20	
	70 µm	EYGA121807RV	115×180 mm	10	
	A-RV type	EYGA091203RV	90×115 mm	20	
	25 µm	EYGA121803RV	115×180 mm	10	
	A-RV type 17 μm	EYGA091202RV	90×115 mm	20	
		EYGA121802RV	115×180 mm	10	
	E-9 type Elastomer 3.0 mm, PGS 70 μm	EYGE0912XB9D	90×115 mm	5	
	E-9 type Elastomer 3.0 mm, PGS 25 µm	EYGE0912XD9D	90×115 mm	5	
SSM Elastomer	E-8 type Elastomer 2.0 mm, PGS 70 μm	EYGE0912XB8D	90×115 mm	5	
3.0, 2.0, 1.0 mm PGS 70, 25 μm	E-8 type Elastomer 2.0 mm, PGS 25 µm	EYGE0912XD8D	90×115 mm	5	
	E-6 type Elastomer 1.0 mm, PGS 70 μm	EYGE0912XB6D	90×115 mm	5	
	E-6 type Elastomer 1.0 mm, PGS 25 µm	EYGE0912XD6D	90×115 mm	5	

Only S type supports 180×230 mm size. (PGS thickness of 17 μm, 10μm does not support as single item)
 ** PGS of 10 μm, 40 μm, 50 μm type is also possible to be made as lamination type.
 *** The above-listed part number is sample part number for testing.

**** Please contact us about your request of custom part number which will be arranged separately.

***** Please contact us if quantity is below Minimum Order Quantity.

Guidelines and precautions regarding the technical information and use of our products described in this online catalog.

- If you want to use our products described in this online catalog for applications requiring special qualities or reliability, or for applications where the failure or malfunction of the products may directly jeopardize human life or potentially cause personal injury (e.g. aircraft and aerospace equipment, traffic and transportation equipment, combustion equipment, medical equipment, accident prevention, anti-crime equipment, and/or safety equipment), it is necessary to verify whether the specifications of our products fit to such applications. Please ensure that you will ask and check with our inquiry desk as to whether the specifications of our products.
- The quality and performance of our products as described in this online catalog only apply to our products when used in isolation. Therefore, please ensure you evaluate and verify our products under the specific circumstances in which our products are assembled in your own products and in which our products will actually be used.
- If you use our products in equipment that requires a high degree of reliability, regardless of the application, it is recommended that you set up protection circuits and redundancy circuits in order to ensure safety of your equipment.
- The products and product specifications described in this online catalog are subject to change for improvement without prior notice. Therefore, please be sure to request and confirm the latest product specifications which explain the specifications of our products in detail, before you finalize the design of your applications, purchase, or use our products.
- The technical information in this online catalog provides examples of our products' typical operations and application circuits. We do not guarantee the non-infringement of third party's intellectual property rights and we do not grant any license, right, or interest in our intellectual property.
- If any of our products, product specifications and/or technical information in this online catalog is to be exported or provided to non-residents, the laws and regulations of the exporting country, especially with regard to security and export control, shall be observed.

<Regarding the Certificate of Compliance with the EU RoHS Directive/REACH Regulations>

- The switchover date for compliance with the RoHS Directive/REACH Regulations varies depending on the part number or series of our products.
- When you use the inventory of our products for which it is unclear whether those products are compliant with the RoHS Directive/REACH Regulation, please select "Sales Inquiry" in the website inquiry form and contact us.

We do not take any responsibility for the use of our products outside the scope of the specifications, descriptions, guidelines and precautions described in this online catalog.