REVISION AN - ECN-23-192164

## REFERENCE INFORMATION FOR STANDARD MATERIAL AND FINISHES FOR BACKSHELLS & BACKSHELL ACCESSORIES

## BACKSHELL MATERIALS

POLAMCO MATERIAL CODE (BT, 60, 70)	RAYCHEM MATERIAL LETTER CODE (TXR)	DESCRIPTION	RoHS V	REACH Compliant
1	A	ALUMINIUM ALLOY TO: 6061-T6 PER SAE AMS-QQ-A-200/8, & 6082-T6 (MIXED BATCHES OF MATERIAL GRADES ARE POSSIBLE UNTIL SEPTEMBER 2023)	✓	✓
'		ALUMINIUM ALLOY TO: 6064-T9 (6262R) AND 6042-T5, 6064-T6, 6026-T6 (mixed batches of material grades are possible until september 2023)	CONTAINS COMPLIANT W 6(b	ITH EXEMPTION
2	В	nickel aluminium bronze to: nes 833 Or bs2874 Ca 104 Or astm C 63200 Or astm b 150	✓	<b>✓</b>
3	D	BRASS TO: BS2874 CZ121, ASTM B16/16M, ASTM B36, ASTM B141, OR ASTM B212	CONTAINS COMPLIANT W 6(	ITH EXEMPTION
4	S	STAINLESS STEEL TO: BS970 302S25, 303S31,	✓	✓
46		STAINLESS STEEL: EN 10088-3 1.4401 (alt. des. 316S31); EN 10088-3 1.4404 (alt. des. 316L)	✓	<b>✓</b>
74		POLYETHERIMIDE (ULTEM) FLUID RESISTANCE TO EIA-364-10F-2014	✓	✓

## COMMON COMPONENT MATERIALS

COMPONENT	MATERIAL					
	SILICONE					
O-RINGS	fluorosilicone					
O-RINGS	FPM (FLUOROCARBON)					
	NITRILE					
SCREWS & WASHERS	STAINLESS STEEL (UNLESS OTHERWISE STATED)					
LANYARD ATTACHMENTS	STAINLESS STEEL (UNLESS OTHERWISE STATED)					

THE STANDARD MATERIALS STATED ABOVE ARE USED FOR THE MAJORITY OF TE CONNECTIVITY BACKSHELLS & BACKSHELL ACCESSORY PRODUCT LINES. HOWEVER, THEY ARE NOT LIMITED TO THESE ITEMS LISTED, PLEASE CONTACT TE CONNECTIVITY WITH YOUR SPECIFIC APPLICATION FOR RECOMMENDED ALTERNATIVES.

	DIMENSIO MILLIMET		DWN: K.K-W	09/02/2018	MATERIAL: N/A			FINISH: N/A				
MILLIMETERS TOLERANCES UNLESS		CHK: R.STYLES	18/06/2020			<b>5</b> 7	<b>E</b> TE	Conne	c tivit	y		
OTHERWISE SPECIFIED:		ECIFIED:	AP∨D: M.PAUL	14/02/2018	PART N			220	 076		•	
	CENEDAL TO		PRODUCT SPEC:		_							
	LINEAR ±0 ANGULAR	GENERAL TOL INEAR <u>+</u> 0,25MM ANGULAR <u>+</u> 1°	-	NAME: MATERIAL AND FINISH DETAILS								
			APPLICATION SPEC:									
			=		SIZE	CAGE CODE	DRAWING N				RESTR!	ICTED TO
40	♠ =		WEIGHT:		Α4	U5792	C-22	0076				
	9		DATA SHEET				SCALE 1:1	SHEET	1 OF	2 [	rev AN	

RESERVED

RIGHTS

ALL

Æ

COPYRIGHT

(0)

В

## MATERIAL & FINISH OPTIONS

9/00	POLAMCO FINISH CODE (BT, 60, 70)	RAYCHEM FINISH CODE (TXR)	MATERIAL	FINISH	SPECIFICATION / DESCRIPTION	COLOUR (SEE NOTES)	SALT SPRAY PERFORMANCE	ELECTRICAL CONDUCTIVITY	OPERATING TEMP. RANGE	RoHS V Compliant	REACH V Compliant
SS	1-B	АВ	ALUMINIUM	CADMIUM	QQ-P-416, TYPE II, CLASS 3 OVER ELECTROLESS NICKEL	OLIVEDRAB	500 HRS	CONDUCTIVE	-65 TO +175°C	*	×
DVG ND	1-KB	-	ALUMINIUM	CADMIUM	QQ-P-416, TYPE II, CLASS 3, OVER ELECTROLESS NICKEL [QUALIFIED TO 85049]	OLIVE DRAB	1000 HRS	CONDUCTIVE	-65TO +175°C	×	×
TROLLED DOCUMENT	1-C 4-C	AC SC	ALUMINIUM STAINLESS STEEL	ELECTROLESS NICKEL	AMS-C-26074, CLASS 4, GRADE B	BRIGHT	48 HRS	CONDUCTIVE	-65 TO +200 °C	✓	✓
	1-CHP	-	ALUMINIUM	HIGH PHOSPHORUS ELECTROLESS NICKEL	HIGH PHOSPHORUS ELECTROLESS NICKEL (FOR SPACE APPLICATION) - RECTANGULAR BACKSHELLS ONLY	BRIGHT	48 HRS	CONDUCTIVE	-65 TO +200 °C	✓	✓
NG IS A C	1-D	AG	ALUMINIUM	ANODISE HARD	mil-a-8625, type III, Class 2 (not suitable for screen termination)	BLACK	500 HRS	NON-CONDUCTIVE	-65TO +175°C	✓	✓
THIS DRAWI	1-G	AK	ALUMINIUM	anodise, Sulphuric	mil-a-8625, type II, class 2 (not suitable for screen termination)	BLACK	500 HRS	NON-CONDUCTIVE	-65 TO +175°C	✓	✓
	4-J 46-J	SJ	STAINLESS STEEL STAINLESS STEEL (316)	PASSIVATE	QQ-P-35 OR MI-S-5002		500 HRS 1000 HRS	CONDUCTIVE	-65 TO +200 °C	✓	✓
	1-KC	AD	ALUMINIUM	HIGH PHOSPHORUS ELECTROLESS NICKEL	AMS-C-26074 OR AMS2404 [QUALIFIED TO 85049]		96 HRS	CONDUCTIVE	-65 TO +200 °C	✓	✓
	1-KZQ	-	ALUMINIUM	ZINC NICKEL PASSIVATE OVER ELECTROLESS NICKEL	DEUTSCH SPECIFICATION: HDS 05- 16182 [QUALIFIED TO 85049]		1000 HRS	CONDUCTIVE	-65 TO +175°C	✓	✓
	1-TN 4-TN	AX SX	ALUMINIUM STAINLESS STEEL	NICKEL PTFE	AS PER DPS-4-336: PTFE OVER HIGH PHOSPHORUS ELECTROLESS NICKEL OVER SULFAMATE NICKEL.	GREY	500 HRS	-	-	✓	✓
	2-U	B/	NICKEL ALUMINIUM BRONZE	AS MACHINED	NO PLATING	BRIGHT	NOT TESTED	CONDUCTIVE	-	✓	✓
	1-Y	-	ALUMINIUM	CADMIUM	YELLOW CHROMATE OVER CADMIUM QQ-P-416, TYPE II, CLASS 2	YELLOW CAD	NOT TESTED	CONDUCTIVE	-	×	×
	1-Y7	-	ALUMINIUM	ELECTROPLATED GOLD	MIL-G-45204 TYPE II, GRAD C. CLASS 0 OVER COPPER IN ACCORDANCE WITH MIL-C-14550	GOLD	NOT TESTED	CONDUCTIVE	-	✓	✓
	2-Z	BW	NICKEL ALUMINIUM BRONZE	UNPLATED	SHOT BLAST FOR NON-REFLECTIVE FINISH		1000 HRS	CONDUCTIVE	-65 TO +200 °C	✓	✓
	1-ZB	AU	ALUMINIUM	ZINC COBALT	OVER ELECTROLESS NICKEL WITH OLIVE DRAB CHROMATE CONVERSION OLIVE DRAB 5		500 HRS	CONDUCTIVE	-65TO +175°C	✓	✓
	1-ZK	A6	ALUMINIUM	ZINC COBALT	OVER ELECTROLESS NICKEL WITH BLACK CHROMATE CONVERSION		350 HRS	CONDUCTIVE	-65TO +175°C	✓	✓
	1-ZN	ΑZ	ALUMINIUM	ZINC NICKEL PASSIVATE OVER ELECTROLESS NICKEL	VER ASTM B 841 CLASS 1 BLA		500 HRS	CONDUCTIVE	-65TO +175°C	✓	✓

FOR ALTERNATIVE MATERIAL / FINISH COMBINATIONS, PLEASE CONTACT TE CONNECTIVITY, BACKSHELL ENGINEERING TEAM.

FINISH NOTES: -

THE COLOUR INDICATED ARE FOR APPROXIMATE COLOUR APPEARANCE FOR REFERENCE ONLY, VARIATIONS OF COLOURS ARE A PART OF THE NORMAL PLATING PROCESS, COLOUR VARIATIONS, BATCH TO BATCH, PART TO PART, COMPONENT TO COMPONENT WITHIN A PART, SHALL NOT BE A CAUSE FOR REJECTION.

FOR EXAMPLE ZINC NICKEL PLATING CAN VARY FROM GREENISH BLACK TO BLACK OF CADMIUM PLATING CAN VARY FROM TANISHGREEN TO DARK GREEN; ETC.

			DWN	09/	/02/2018	MATERIAL	-	HEAT TREAT	
			K'K-M			N/A		N/A	
	DIMENSIONS:	TOLERANCES UNLESS	СНК	18/	/06/2020				
25	mm	O PLC ±0,40	RISTYLES	4.4	/0.0./0.04.0			TE Connec	-+ ,, +,,
	<b>\$</b> [	1 PLC ±0,40 2 PLC ±0,20	M.PAUL	147	/02/2018	=7		IL CUTIFIE	_ (1)1 ( y
)M	\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	ANGLES ±1° ALL FILLETS 0,4 MAX	NAME	MATE	ERIAL A	ND FINISH	H DE	TAILS	
	ALL DIAMETERS 000, SURFACE FINISH Ra1.6 M. REMOVE ALL BURRS AND	_	scale size A	3 PART		\$0076	SHE	2 of 2	AN

8 7 6 5 4 3