### **General Specifications**

#### **GENERAL DESCRIPTION**


With increased requirements from the automotive industry for additional component robustness, AVX recognized the need to produce a MLCC with enhanced mechanical strength. It was noted that many components may be subject to severe flexing and vibration when used in various under the hood automotive and other harsh environment applications.

To satisfy the requirement for enhanced mechanical strength, AVX had to find a way of ensuring electrical integrity is maintained whilst external forces are being applied to the component. It was found that the structure of the termination needed to be flexible and after much research and development, AVX launched FLEXITERM®. FLEXITERM® is designed to enhance the mechanical flexure and temperature cycling performance of a standard ceramic capacitor with an X7R dielectric. The industry standard for flexure is 2mm minimum. Using FLEXITERM®, AVX provides up to 5mm of flexure without internal cracks. Beyond 5mm, the capacitor will generally fail "open".

As well as for automotive applications FLEXITERM® will provide Design Engineers with a satisfactory solution when designing PCB's which may be subject to high levels of board flexure.

#### **PRODUCT ADVANTAGES**

- High mechanical performance able to withstand, 5mm bend test quaranteed.
- Increased temperature cycling performance, 3000 cycles and beyond.
- Flexible termination system.
- Reduction in circuit board flex failures.
- Base metal electrode system.
- Automotive or commercial grade products available.



#### **APPLICATIONS**

#### **High Flexure Stress Circuit Boards**

 e.g. Depanelization: Components near edges of board.


#### **Variable Temperature Applications**

- Soft termination offers improved reliability performance in applications where there is temperature variation.
- e.g. All kind of engine sensors: Direct connection to battery rail.

#### **Automotive Applications**

- Improved reliability.
- Excellent mechanical performance and thermo mechanical performance.

#### **HOW TO ORDER**



NOTE: Contact factory for availability of Tolerance Options for Specific Part Numbers.

### **Specifications and Test Methods**

#### **PERFORMANCE TESTING**

#### AEC-Q200 Qualification:

• Created by the Automotive Electronics Council

 Specification defining stress test qualification for passive components


#### **Testing:**


Key tests used to compare soft termination to


- AEC-Q200 qualification:
- Bend Test


### • Temperature Cycle Test **BOARD BEND TEST RESULTS**

AEC-Q200 Vrs AVX FLEXITERM® Bend Test









#### **TABLE SUMMARY**

Typical bend test results are shown below:


Conventional Termination	FLEXITERM®
>2mm	>5mm
>2mm	>5mm
>2mm	>5mm
	Conventional Termination >2mm >2mm >2mm >2mm

#### TEMPERATURE CYCLE TEST PROCEDURE

#### Test Procedure as per AEC-Q200:

The test is conducted to determine the resistance of the component when it is exposed to extremes of alternating high and low temperatures.

- Sample lot size quantity 77 pieces
- TC chamber cycle from -55°C to +125°C for 1000 cycles
- Interim electrical measurements at 250, 500, 1000 cycles
- Measure parameter capacitance dissipation factor. insulation resistance




#### **BOARD BEND TEST PROCEDURE**

According to AEC-Q200

Test Procedure as per AEC-Q200: Sample size: 20 components Span: 90mm Minimum deflection spec: 2 mm • Components soldered onto FR4 PCB (Figure 1)

- Board connected electrically to the test equipment
- (Figure 2)



MOUNTING al-lo CONTROL


Fig 1 - PCB layout with electrical connections

Fig 2 - Board Bend test equipment

### **AVX ENHANCED SOFT TERMINATION BEND TEST PROCEDURE**

#### **Bend Test**

The capacitor is soldered to the printed circuit board as shown and is bent up to 10mm at 1mm per second:




- The board is placed on 2 supports 90mm apart (capacitor side down)
- The row of capacitors is aligned with the load stressing knife





- The load is applied and the deflection where the part starts to crack is recorded (Note: Equipment detects the start of the crack using a highly sensitive current detection
- The maximum deflection capability is 10mm


## **Specifications and Test Methods**

#### **BEYOND 1000 CYCLES: TEMPERATURE CYCLE TEST RESULTS**










Soft Term - No Defects up to 3000 cycles

AEC-Q200 specification states 1000 cycles compared to AVX 3000 temperature cycles.

#### **FLEXITERM® TEST SUMMARY**


- Qualified to AEC-Q200 test/specification with the exception of using AVX 3000 temperature cycles (up to +150°C bend test guaranteed greater than 5mm).
- FLEXITERM® provides improved performance compared to standard termination systems.
- Board bend test improvement by a factor of 2 to 4 times.
- Temperature Cycling:
  - 0% Failure up to 3000 cycles
  - No ESR change up to 3000 cycles

#### WITHOUT SOFT TERMINATION



Major fear is of latent board flex failures.

#### WITH SOFT TERMINATION



## X8R Dielectric Capacitance Range

	SIZE	0	603	08	805	1206				
	Soldering	Reflo	w/Wave	Reflow	v/Wave	Reflow/Wave				
	WVDC	25V	50V	25V	50V	25V	50V			
271	Cap 270	G	G							
331	(pF) 330	G	G	J	J					
471	470	G	G	J	J					
681	680	G	G	J	J	İ				
102	1000	G	G	J	J	J	J			
152	1500	G	G	J	J	J	J			
182	1800	G	G	J	J	J	J			
222	2200	G	G	J	J	J	J			
272	2700	G	G	J	J	J	J			
332	3300	G	G	J	J	J	J			
392	3900	G	G	J	J	J	J			
472	4700	G	G	J	J	J	J			
562	5600	G	G	J	J	J	J			
682	6800	G	G	J	J	J	J			
822	8200	G	G	J	J	J	J			
103	Cap 0.01	G	G	J	J	J	J			
123	(μF) 0.012	G	G	J	J	J	J			
153	0.015	G	G	J	J	J	J			
183	0.018	G	G	J	J	J	J			
223	0.022	G	G	J	J	J	J			
273	0.027	G	G	J	J	J	J			
333	0.033	G	G	J	J	J	J			
393	0.039	G	G	J	J	J	J			
473	0.047	G	G	J	J	J	J			
563	0.056	G		N	N	М	M			
683	0.068	G		N	N	М	М			
823	0.082			N	N	М	M			
104	0.1			N	N	М	М			
124	0.12			N	N	М	М			
154	0.15			N	N	М	М			
184	0.18			N		M	M			
224	0.22			N		М	М			
274 334	0.27					M	M M			
	0.33					М	M			
394	0.39					M				
474	0.47	_				М				
684	0.68									
824	0.82									
105		OFV	FOV	051/	F0\/	051/	FO' /			
	WVDC	25V	50V	25V	50V	25V	50V			
	SIZE		603	30	305	1206				

Letter	А	С	Е	G	J	K	М	N	Р	Q	Χ	Υ	Z
Max.	0.33	0.56	0.71	0.90	0.94	1.02	1.27	1.40	1.52	1.78	2.29	2.54	2.79
Thickness	(0.013)	(0.022)	(0.028)	(0.035)	(0.037)	(0.040)	(0.050)	(0.055)	(0.060)	(0.070)	(0.090)	(0.100)	(0.110)
			PAPER						EMBC	SSED			

AEC-Q200 Qualified

## X7R Dielectric Capacitance Range

				0402	2				0603	3					30	305						1206	6				12	10		18	312		2220	
So	lderir	ng	Ret	flow/W	lave			Re	flow/M	lave					Reflov	v/Wave	9				Re	flow/M	lave				Reflov	v Only		Reflov	v Only	R€	eflow O	nly
		Ť	16V	25V	50V	10V	16V	25V	50V	100V	200V	250V	16V	25V	50V	100V	200V	250V	16V	25V	50V	100V	200V	250V	500V	16V	25V	50V	100V	50V	100V		50V	
221	Cap	220	С	С	С																													
271	(pF)	270	С	С	С																										$\vdash$		$\vdash$	
331		330	С	С	С																													
391		390	С	С	С																													
471		470	С	С	С																												П	
561		560	С	С	С																													
681		680	С	С	С																													
821		820	С	С	С																													
102		1000	С	С	С		G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K			
182		1800	С	С	С		G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K			
222		2200	С	С	С		G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K			
332		3300	С	С	С		G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K			
472		4700	С	С	С		G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K	$\perp$	<u> </u>	
103	Сар		С				G	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	J	J	K	K	K	K	K	K		igsquare	
123		0.012	С	_	_	<b>⊢</b>	G	G	G		_	_	J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K	Ь—	<b></b> '	—
153		0.015	С			_	G	G	G				J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K			_
183		0.018	С			_	G	G	G				J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K	_	<u> </u>	_
223		0.022	С		1	_	G	G	G				J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K			_
273		0.027	С		_	_	G	G	G	_			J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K	_	<u> </u>	_
333 473		0.033	С		_	┞	G	G	G				J	J	J	М	J	J	J	J	J	J	J	J		K	K	K	K	K	K	_	<b></b> '	-
563		0.047			-	├	G	G	G				J	J	J	M	J	J	J	J	J	M	J	J		K	K	K	K	K	K	_	<b></b> -	-
683		0.068			-	├	G	G	G				J	J	J	M		_	J	J	J	M	J	J		K	K	K	M	K	K	$\vdash$	<b>-</b>	<u> </u>
823		).082			-	-	G	G	G	_			J	_	J	M			-	J	J	M	J	J		K	K	K	M	K	K	_		-
104	U	0.1	_		-	$\vdash$	G	G	G				J	J	J	M		-	J	J	J	M	J	J	_	K	K	K	M	K	K	$\vdash$	₩	-
124		0.12				-	u	u	u				J	J	M	N			J	J	M	M	U	U		K	K	K	P	K	K		$\vdash$	-
154		0.12			-	├		-		-			M	N	M	N	_	-	J	J	M	M	_			K	K	K	P	K	K	$\vdash$	$\vdash$	├
224		0.22			-	G		-					M	N	M	N			J	M	M	Q	-			M	M	M	P	M	M	$\vdash$	$\vdash$	<del></del>
334		0.33	_		-	u	_	_					N	N	M	N			J	M	P	Q	_			P	P	P	Q	X	X		$\vdash$	$\vdash$
474		0.47	-	-	1	+	+	<u> </u>	-		-		N	N	M	I N		<del> </del>	M	M	P	Q			-	P	P	P	Q	X	X	$\vdash$	$\vdash$	$\vdash$
684		0.68		$\vdash$	+-	$\vdash$	+	$\vdash$	$\vdash$	$\vdash$			N	N	N				M	Q	0	Q				P	P	Q	X	X	X	$\vdash$	$\vdash$	$\vdash$
105		1			1	$\vdash$	<del>                                     </del>	<del>                                     </del>					N	N	N		1		M	Q	T Q	Q				P	Q	Q	X	X	X		$\vdash$	$\vdash$
155		1.5			+		+	_		$\vdash$			<u> </u>				+		Q	Q	T Q					P	Q	Z	Z	X	X		$\vdash$	$\vdash$
225		2.2			+		<u> </u>			<u> </u>	<u> </u>					<u> </u>	+		Q	Q	Q					X	Z	Z	Z	Z	Z		+-	$\vdash$
335		3.3				t	<del>                                     </del>	<u> </u>											Q	Q	<u> </u>					Х	Z	Z	Z	Z		$\vdash$	$\vdash$	
475		4.7			1	t		t									1		Q	Q			t -			X	Z	Z	Z	Z			$\vdash$	Z
106		10				-	_	_		$\vdash$						$\vdash$							_			Z	Z				$\vdash$		Z	Z
226		22				i –																									T	Z	$\vdash$	
			16V	25V	50V	10V	16V	25V	50V	100V	200V	250V	16V	25V	50V	100V	200V	250V	16V	25V	50V	100V	200V	250V	500V	16V	25V	50V	100V	50V	100V	25V	50V	100V
				0402	2				0603	}					30	305						1206					12	10		18	312		2220	
Le	tter		А		(	,		E		G		J		K		М		N			P		Q		Χ		Υ		Z					
	lax.		0.30	3	0.8			<u>-</u> .71		0.90		0.94		1.02		1.2		1.4			.52		.78	1 9	2.29		2.54		2.79	9				
	Max. 0.33				1221		 N28)		.035)		1 037	\	(n na		(O OF		(0.0			16N		070)		 . (1901)		1.0 i	٨	(0.11						

Letter	А	С	Е	G	J	K	М	N	Р	Q	Χ	Υ	Z		
Max.	0.33	0.56	0.71	0.90	0.94	1.02	1.27	1.40	1.52	1.78	2.29	2.54	2.79		
Thickness	(0.013)	(0.022)	(0.028)	(0.035)	(0.037)	(0.040)	(0.050)	(0.055)	(0.060)	(0.070)	(0.090)	(0.100)	(0.110)		
			DADED			EMPOSSED									